

# SOLSPERSE<sup>®</sup> 64000

A 100% active polymeric dispersant

<b>Applications</b>	Universal decorative tinters						
<b>Performance</b>	<p>SOLSPERSE 64000 is a 100% active polymeric dispersant, which will improve pigment dispersion and stability in universal colorants.</p> <p>In the above applications, the following benefits are achieved:</p> <ul style="list-style-type: none"><li>• Effective pigment stability</li><li>• Compatibility with a wide range of decorative binders</li><li>• Excellent colour compatibility and flocculation resistance</li><li>• For APE and VOC-free universal colorants</li></ul>						
<b>Incorporation</b>	The SOLSPERSE 64000 should be dissolved in the millbase water before the addition of pigments.						
<b>Addition levels</b>	Addition levels should be based on the surface area of the pigment / filler. A typical dosage level for an organic pigment is 30-40% based on weight of the pigment. Please refer to the Application Data Sheet for formulation guidance.						
<b>Typical properties</b>	<table border="1"><tr><td>Appearance</td><td>Amber liquid</td></tr><tr><td>Flash point (°C)</td><td>&gt;101</td></tr><tr><td>Density (g/cm<sup>3</sup>)</td><td>0.98</td></tr></table>	Appearance	Amber liquid	Flash point (°C)	>101	Density (g/cm <sup>3</sup> )	0.98
Appearance	Amber liquid						
Flash point (°C)	>101						
Density (g/cm <sup>3</sup> )	0.98						
<b>Packaging and storage</b>	<p>SOLSPERSE 64000 is packed in 25Kg steel drums.</p> <p>Shelf life: 2 years.</p> <p>For storage, please refer to the MSDS.</p>						
<b>Regulatory status</b>	For detailed information, please refer to the MSDS.						

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol, Ltd. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Lubrizol, Ltd.'s direct control. THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

Reference: HD0/1/099-GB

© Date: 07/2008

**Lubrizol, Ltd.**  
Hexagon Tower, Blackley  
Manchester M9 8ZS, United Kingdom  
Tel.: +44-(0)161-721-2004  
[www.lubrizolcoatings.com](http://www.lubrizolcoatings.com)